

Precipitate-hardened NiAl alloys as innovative gaseous field ion sources

M. S. Mousa*, K. F. Russell and M. K. Miller

Metals and Ceramics Division, Oak Ridge National Laboratory, P.O. Box 2008, Oak Ridge, TN 37831-6376, USA

*On sabbatical leave from the Department of Physics, Mu'tah University, Al-Karak, Jordan

Gaseous field ion sources (GFIS) exhibit small energy spreads (~ 1 eV) and a virtual source size of ~ 2 nm. A GFIS can be operated with inert gases and therefore has potential applications in mask repair applications. However, gaseous field ion sources have rarely been employed in focussed ion beam (FIB) systems due to their relatively low angular current densities. The angular intensity of a GFIS may be increased by confining the ion emission to a small area on the emitter surface.

A new approach producing high current densities is under development in which an ion beam is confined to the region above an ultrafine precipitate on the surface of a needle-shaped tip. In this approach, the base of the emitter is used to attract and thermally accommodate atoms from the gas over the tip surface. However, the experimental conditions are selected to ensure that no ion emission occurs from the base of the tip. These gas atoms then are drawn over the surface to the high field region above the precipitate where they are ionized and produce the ion beam. The extent of the precipitate exposed on the surface of the emitter may be manipulated by field evaporation thereby providing a simple method of optimizing the source size.

A precipitation hardened alloy has been designed and fabricated that contains a high density of ultrafine tungsten carbide precipitates in a B2-ordered NiAl matrix. The sources are produced from this alloy by cutting the bulk material into 0.25 mm square bars and electropolishing these bars into needle-shaped tips. The precipitates have bright contrast in the field ion images and an average size of ~ 5 nm. The morphology of these precipitates varied between roughly lenticular or oblate plates to spherical. Careful evaporation of the tip enabled the variation of size of the source. Atom probe analysis has revealed that the refractory precipitates are WC and W_2C carbides. No nickel or aluminum was found in the carbides. The emission current-voltage (I-V) characteristics of these sources have been determined as a function of a variety of parameters. Such characteristics provide important information about the mechanisms controlling the emission process.

Research in the Oak Ridge National Laboratory SHaRE User facility was sponsored by the Division of Materials Sciences, U. S. Department of Energy, under contract DE-AC05-00OR22725 with UT-Battelle, LLC. and the Defense Advanced Research Projects Agency, MIPR 00-B538 under DOE proposal number 1868-EE11-X1.